

# Primers and Fillers

**LESONAL**



## Mixing Ratios by Weight

PRODUCT	1 Litre R.F.U.	0.5 Litre R.F.U.	0.3 Litre R.F.U.	0.2 Litre R.F.U.
<i>2K Filler 540 sanding mixture</i>				
2K Filler 540	1126 g	563 g	338 g	225 g
Universal Hardener (any)	141 g	71 g	42 g	28 g
Multi Thinner (any)	128 g	64 g	38 g	25 g
<i>2K Filler 540 non sanding mixture</i>				
2K Filler 540	946 g	473 g	284 g	189 g
HS Hardener 420	107 g	54 g	32 g	21 g
Thinner 540 Non Sanding	248 g	124 g	74 g	50 g
2K High Build Filler	1093 g	547 g	328 g	219 g
Universal Hardener (any)	141 g	71 g	42 g	28 g
Multi Thinner (any)	128 g	64 g	38 g	25 g
1K Etch Primer	661 g	331 g	198 g	132 g
Multi Thinner (any)	300 g	150 g	90 g	60 g
2K Epoxy Primer	834 g	417 g	250 g	167 g
Hardener Epoxy Primer	241 g	121 g	72 g	48 g
Multi Thinner (any)	189 g	95 g	57 g	38 g
2K Universal Plastic Primer	825 g	413 g	248 g	165 g
Hardener Uni. Plastic Primer	123 g	62 g	37 g	25 g
Multi Thinner (any)	225 g	113 g	68 g	45 g